



SPLENDORGEL EW

description

Extra white ultra-fine papers and boards with a very smooth and velvety surface. Clear look-through. Made of pure E.C.F. pulp, certify FSC. Substances over 230g are on-machine laminated in the formation stage. Characteristics provide perfect on-press performance, excellent ink-yield and brilliant printed results. In 45x64* format, substances 85g 100g and 115g are produced in "Litholaser" version, therefore suitable for offset pre-printing and subsequent printing on toner-based laser printers.

range

size	grain	substance							
45x64	LG	85	100	115	230	270	300	340	
64x88	LG	85	100						
71x100	LG	85	100	115	140	160	190	230	270 300 340

technical features

ref. standard/instrument
unit of measure

substance	VSA	opacity	roughness	tensile strength	
ISO 536	ISO 534	ISO 2471	ISO 8791-2	ISO 1924	
g/m ²	cm ³ /g	%	ml/min	long±10%	cross±10%
85 ± 3%	1,1	88 ± 2	70 ± 20	5,2	3,2
100 ± 4%	1,1	90 ± 2	70 ± 20	5,9	3,9
115 ± 4%	1,1	92 ± 2	70 ± 20	7,2	4,2
140 ± 4%	1,1	94 ± 2	70 ± 20	8,5	4,5
160 ± 5%	1,1	–	70 ± 20	9,1	5,2
190 ± 5%	1,1	–	70 ± 20	10,4	5,9
230 ± 5%	1,1	–	60 ± 20	13,7	7,2
270 ± 5%	1,1	–	60 ± 20	15	7,8
300 ± 5%	1,1	–	60 ± 20	16,3	8,5
340 ± 5%	1,1	–	60 ± 20	–	–

Brightness (col. Extra White) - ISO 2470 (R457) - 112% ± 2
Relative Humidity 50% ± 5 ref. TAPPI 502-98

ecological features



The mark of responsible forestry

ELEMENTAL
CHLORINE
FREE
GUARANTEED



notes

The product is completely biodegradable and recyclable.
Special runs available upon request.



Envelopes available on stock.

The Company reserves the right to modify the technological features of the product in relation to market requirements.

Splendorgel E.W. is excellent for packaging, coordinated graphic materials, labels, covers, inserts, de luxe brochures. In versions 85-100 gr. it is particularly suitable for letterheads and writing papers.

applications

Can be used without problems with the main printing systems: letterpress, offset, blind embossing, hot foil stamping, thermography and screen printing. The macro-porous surface suggests the use of oxidative drying inks. Good chromatic and tone performance, ink load, dot gain and printing contrast are at the highest levels obtainable from uncoated papers.

printing
suggestions

Varnishing and plastic laminating must be assessed in advance. The varnishing coated with an offset machine is almost fully absorbed and therefore does not improve gloss or protection. Screen-printing varnishing achieves better results, although it is often necessary to perform two shots to achieve a distinctly evident result. The surface roughness typical of uncoated papers may give rise to micro defects with plastic laminating caused by incomplete adhesion of the film to the substrate.

converting
suggestions

Good results with major processing operations such as: cutting, die-cutting, scoring, folding and glueing.